



Accura[®] 50 plastic

for use with solid-state stereolithography (SLA[®]) systems

Simulate the properties and appearance of molded ABS with this durable, accurate and versatile plastic.



APPLICATIONS

- Functional components for assemblies, mock-ups and test for many uses, including:
 - Enclosures, covers and cases for consumer goods
 - Toys
 - Cellular/mobile telephones
 - Electronic components: connectors, interconnects, routing enclosures, etc.
 - Automotive design elements: dash boards, air conditioning vents, etc.
- Accurate, durable master patterns for RTV or silicone molding
- Limited snap-fits and assemblies
- Simulate a molded part
- Concept models
- Marketing models

FEATURES

- Durable and stiff
- Outstanding accuracy w/out shrinkage related distortion
- Choice of grey or natural colors
- Fully developed and tested build styles

BENEFITS

- Produce ABS like parts without machining or molding
- Color selection produces parts that have the appearance of molded plastic
- Rigidity holds shape on thin walls, but flexes for snap fit assemblies
- Produces parts that meet tolerances
- Produces parts that are faithful to the CAD
- Maximize reliability with no user R&D

Accura[®] 50 plastic

For use with solid-state stereolithography (SLA[®]) systems


"Accura 50 is a versatile, reliable material that is the best we've seen in our more than 10 years in business. We've experienced a 100% build success rate which saves us time and money. It is an excellent general-use material with ABS-like properties that is as good for models, snap-fits and functional prototypes as it is for master patterns. This provides us with greater flexibility to meet our customers' needs".

– Ron Belknap - Managing Partner, ProtoCAM

Nine piece Accura 50 grey and natural prototype assembly.



Accura 50 plastic is a tough, resilient material.



Accura 50 natural plastic material.




Printer assembly of production (blue) and Accura 50 grey and natural plastic parts.



Accura 50 plastic looks like a molded ABS part.



Pair of dishwasher components (grey and natural) produced for functional testing.



TECHNICAL DATA

Liquid Material

MEASUREMENT	CONDITION	VALUE:
Appearance		Opaque natural or opaque grey
Liquid Density	@ 25 °C (77 °F)	1.14 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.21 g/cm ³
Viscosity	@ 30 °C (86 °F)	600 cps
Penetration Depth (Dp) *		4.5 mils
Critical Exposure (Ec) *		9.0 mJ/cm ²
Tested Build Styles		FAST [™] , EXACT [™] , Exact HR

Post-cured Material

MEASUREMENT	CONDITION	VALUE:
Tensile Strength	ASTM D 638	48 - 50 MPa (7,030 - 7,240 PSI)
Tensile Modulus	ASTM D 638	2,480 - 2,690 MPa (360 - 390 KSI)
Elongation at Break (%)	ASTM D 638	5.3 - 15.0 %
Flexural Strength	ASTM D 790	72 - 77 MPa (10,400 - 11,200 PSI)
Flexural Modulus	ASTM D 790	2,210 - 2,340 MPa (320 - 340 KSI)
Impact Strength (Notched Izod)	ASTM D 256	16.5 - 28.1 J/m (0.31 - 0.51 ft-lbs/in)
Heat Deflection Temperature	ASTM D 648	
	@ 66 PSI	49 - 53 °C (120 - 127 °F)
	@ 264 PSI	43 - 46 °C (109 - 115 °F)
	@ 66 PSI with 160 °C Thermal Postcure	74 - 80 °C (165 - 176 °F)
Hardness, Shore D		86
Co-efficient of Thermal Expansion	ASTM E 831-93	
	TMA (T<T _g , 0 - 20°C)	73 x 10 ⁻⁶ m/m °C
	TMA (T>T _g , 90 - 150°C)	164 x 10 ⁻⁶ m/m °C
Glass Transition (T _g)	DMA, E''	62 °C (144 °F)

* Dp/Ec values are the same on all systems.



SYSTEMS

TRANSFORM YOUR PRODUCTS

3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: 803.326.4080
Toll-free: 800.889.2964
Fax: 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. EXACT, FAST and QuickCast are trademarks, and the 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.