

Optimised for the rapid and automated production of patterns and master moulds for jewellery manufacturing.



Left: Produce models, master patterns, design alternatives, or size variations in a single build. This platform of 90 rings was built in 16.2 hours, automatically.
Right: Amethyst models (center) can be plated (top and bottom) or painted.

APPLICATIONS

- Patterns for use with low and high vulcanizing rubber moulding
- High resolution concept models

FEATURES

- Outstanding accuracy
- Exceptional detail
- High thermal resistance
- Deep purple colour
- Low ash formulation

BENEFITS

- Parts are accurately produced in X, Y and Z
- Small details are faithfully reproduced
- Patterns are compatible with high temperature rubber moulding operations
- Produces parts in a high contrast colour for easy identification
- Material can be burned out for direct casting

Accura® Amethyst™ material

For use with Viper™ SLA® systems

A high-resolution casting pattern is produced on the Viper SLA system using Amethyst material.



Rubber moulding is used to create multiple wax patterns for casting.



The final production ring.



Images courtesy of Alberto Bolzonella

TECHNICAL DATA

Liquid Material

MEASUREMENT	CONDITION	VALUE:
Appearance		Purple
Liquid Density	@ 25 °C (77 °F)	1.1 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.23g/cm ³
Viscosity	@ 30 °C (86 °F)	350 cps
Penetration Depth (Dp)		3.7 mils
Critical Exposure (Ec)		14.4 mJ/cm ²
Tested Build Styles		FAST™, EXACT™, Exact HR

Post-cured Material

MEASUREMENT	CONDITION	VALUE:
Tensile Strength	ASTM D 638	22 - 38 MPa (3130 - 5450 PSI)
Tensile Modulus	ASTM D 638	3514 - 3996 MPa (510 - 580 PSI)
Elongation at Break (%)	ASTM D 638	0.56 - 1.04 %
Flexural Strength	ASTM D 790	87 - 125 MPa (12700 - 18100 PSI)
Flexural Modulus	ASTM D 790	3652 -3721 MPa (530 - 540 PSI)
Impact Strength (Notched Izod)	ASTM D 256	9 - 12 J/m (0.16 - 0.23 ft-lbs/in)
Heat Deflection Temperature	ASTM D 648	
	@ 66 PSI	77 °C (170.6 °F)
	@ 264 PSI	62 °C (143.6 °F)
Hardness, Shore D		87
Co-efficient of Thermal Expansion	ASTM E 831-93	
	TMA (T<Tg, 0 - 20°C)	57 x 10 ⁻⁶ m/m °C
	TMA (T>Tg, 90 - 150°C)	133 x 10 ⁻⁶ m/m °C
Glass Transition (Tg)	DMA, E''	103 °C (217.4 °F)



3D Systems Europe Ltd.

Mark House, Mark Road
Hemel Hempstead
Herts HP2 7UA - UK
www.3dsystems.com

Tel: (+44) 1442 282 600
Fax: (+44) 1442 282 601
marketing.uk@3dsystems.com
Nasdaq: TDSC

3D Systems GmbH

Postfach 12 02 07
D-64239 Darmstadt
Germany

Tel: (+49) 6151 357 0
Fax: (+49) 6151 357 333
info@3dsystems-europe.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2006 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. Amethyst, FAST and EXACT are trademarks, and the 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.