









# Figure 4\* Material Properties and Applications Guide

		SUITABILITY FOR PART GEOMETRIES (% PRINTABILITY POTENTIAL)*								MECHANICAL PROPERTIES			
										Tensile Modulus MPA	Elongation @ Break %	Impact Strength (Notched) J/M	HDT @ 0.455 MPA °C
PROTOTYPING AND DESIGN VERIFICATION	TOUGH-GRY 10	75	85	45	75	85	35	15	25	2180	25	29	59
	TOUGH-GRY 15	75	85	75	75	85	35	15	25	2120	35	32	59
	TOUGH-BLK 20	95	90	85	85	90	75	35	65	1780	36	27	55
	FLEX-BLK 10	85	85	55	75	85	75	15	35	1400	104	55	52
	FLEX-BLK 20	90	90	90	90	95	95	55	85	1150	76	91	41
PRODUCTION	PRO-BLK 10	95	95	95	95	95	95	65	95	2320	12	24	70
	Rigid White	95	95	95	95	95	95	95	95	2100	20	21	65
	Rigid Gray	95	95	95	95	95	95	95	95	2400	30	21	72
	Tough 65C Black	90	95	90	95	95	95	95	95	1700	35	31	70
	Tough 60C White	90	95	90	95	95	95	95	95	1500	23	34	65
	High Temp 150C Black	95	95	95	95	95	95	95	95	2600	4	10	>150
	HI TEMP 300-AMB	95	95	90	95	95	95	65	95	4100	2.3	10	300
	MED-AMB 10	95	95	90	95	85	95	65	90	2765	4	18	119
	MED-WHT 10	95	95	90	95	85	95	65	90	3090	3	17	102
	RUBBER-65A BLK	50	50	65	90	85	85	65	65	23	126	8.5**	65***
	EGGSHELL-AMB 10		98	95		95				2765	5	15	89
APPLICATION SPECIFIC	RUBBER-BLK 10	80	80	85	95	85	90	65	90	540	80	76**	97***
	ELAST-BLK 10	75	75	60	90	85	85	40	65	3.6	83	11**	65***

\* Top 8 types of part geometries based on years of additive experience. Each part was printed with the suite of Figure 4 materials and assigned a % of parts in that category that the material was well suited for producing.

\*\* Tear Strength Type-C kN/m

\*\*\* Shore A Hardness

## RATING SYSTEM

- = VERY HIGH
- = HIGH
- = MEDIUM
- = LOW

		PERFORMANCE							NOTES
		Long Term Indoor Environmentally Stable	Long Term Outdoor Environmentally Stable	Differential Shrink	Bottom Surface	Warp	1st Article Success	Supports	
PROTOTYPING AND DESIGN VERIFICATION	TOUGH-GRY 10			● ● ●	● ● ●	● ● ●	● ● ●	● ● ● ●	<ul style="list-style-type: none"> <li>Fast printing prototyping material</li> <li>Good surface quality for prototyping</li> <li>Light gray material good for contrast and definition</li> </ul>
	TOUGH-GRY 15			● ● ●	● ● ●	● ● ●	● ● ●	● ● ● ●	<ul style="list-style-type: none"> <li>Midline mechanical properties for prototyping including modulus, elongation, and notch impact</li> <li>Good surface quality for prototyping</li> </ul>
	TOUGH-BLK 20	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Long-term stable material for UV and humidity</li> <li>Better accuracy from low differential shrink &amp; bottom surface quality</li> <li>No settling in resin tray</li> </ul>
	FLEX-BLK 10			● ● ● ● ●	● ● ●	● ● ● ● ●	● ● ●	● ● ●	<ul style="list-style-type: none"> <li>Long term stable material for UV and humidity</li> <li>Better accuracy from low differential shrink and bottom surface quality</li> <li>Easier to clean</li> </ul>
	FLEX-BLK 20	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Faster printing FLEX material good for prototyping</li> </ul>
PRODUCTION	PRO-BLK 10	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Best Figure 4 Material performance for 1st article success</li> <li>Long term stable material for UV and humidity</li> <li>Better accuracy from low differential shrink &amp; bottom surface quality</li> </ul>
	Rigid White	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Biocompatible, capable of meeting ISO 10993-5 and -10 standards for cytotoxicity, sensitization and irritation</li> <li>Long term stable material for UV and humidity</li> </ul>
	Rigid Gray	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Long term stable material for UV and humidity</li> <li>Better accuracy from low differential shrink and bottom surface quality</li> </ul>
	Tough 65C Black	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Long term stable material for UV and humidity</li> <li>Better accuracy from low differential shrink and bottom surface quality</li> </ul>
	Tough 60C White	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Biocompatible, capable of meeting ISO 10993-5 and -10 standards for cytotoxicity, sensitization and irritation</li> <li>Long term stable material for UV and humidity</li> </ul>
	High Temp 150C Black	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>UL 94 V0 @ 2mm, 3mm and FST 2mm, 3mm capable</li> <li>Long term stable material for UV and humidity</li> </ul>
	HI TEMP 300-AMB			● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	● ● ● ● ●	<ul style="list-style-type: none"> <li>Very high HDT at both low and high pressure (&gt;300 °C)</li> <li>Better accuracy from low differential shrink &amp; bottom surface quality</li> </ul>

Note: Not all products and materials are available in all countries – please consult your local sales representative for availability

#### RATING SYSTEM



		PERFORMANCE							NOTES
		Long Term Indoor Environmentally Stable	Long Term Outdoor Environmentally Stable	Differential Shrink	Bottom Surface	Warp	1st Article Success	Supports	
PRODUCTION	MED-AMB 10	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	<ul style="list-style-type: none"> <li>• Biocompatible, capable of meeting ISO 10993-5 &amp; -10 standards for cytotoxicity, sensitization and irritation</li> <li>• Better accuracy from low differential shrink &amp; bottom surface quality</li> </ul>
	MED-WHT 10	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	<ul style="list-style-type: none"> <li>• Biocompatible, capable of meeting ISO 10993-5 &amp; -10 standards for cytotoxicity, sensitization and irritation</li> <li>• Better accuracy from low differential shrink &amp; bottom surface quality</li> </ul>
	RUBBER-65A BLK	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	<ul style="list-style-type: none"> <li>• Long term stable material for UV and humidity</li> <li>• Biocompatible, capable of meeting ISO 10993-5 and -10 standards for cytotoxicity, sensitization, and irritation</li> </ul>
	EGGSHELL-AMB 10			●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	<ul style="list-style-type: none"> <li>• Easily breaks away from the injected material once cured</li> <li>• Material is compatible with many platinum and tin silicones</li> </ul>
APPLICATION SPECIFIC	RUBBER-BLK 10	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●●●	●●●	<ul style="list-style-type: none"> <li>• High tear strength makes a very tough malleable material</li> <li>• Long term stable material for UV and humidity</li> <li>• Better accuracy from low differential shrink &amp; bottom surface quality</li> </ul>
	ELAST-BLK 10			●●●●●	●●●●●	●●●●●	●●●	●●●	<ul style="list-style-type: none"> <li>• Low tear strength combined with low tensile modulus makes parts easy to tear</li> </ul>

**RATING SYSTEM**

●●●●● = HIGH  
 ●●●●● = MEDIUM  
 ●●● = LOW

Note: Not all products and materials are available in all countries – please consult your local sales representative for availability

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2021 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo and Figure 4 are registered trademarks of 3D Systems, Inc.

[www.3dsystems.com](http://www.3dsystems.com)

3DS-40111E 08-21